

RTHR0146 (1235/98)
D12/D4989
KB/da-co-KB

COPY

These claims
are not to
be entered.
RS 12/12/03

CORRESPONDING EP CLAIMS

Claims

- 5 1. A pressure can for producing polyurethane insulating foams with
fire-retardant properties comprising a prepolymer composition which consists of
a prepolymer component with at least one PU prepolymer with a content of
NCO-groups of 4 to 20 wt% and usual additives, as well as a propellant
10 component, wherein the prepolymer component has a content of 5 to 40 wt%,
based on the prepolymer component, of softening phosphates and/or
phosphonates with the formulae $O=P(OR)_3$ and $O=P(OR)_2R$, wherein R,
identically or differently, means aryl, alkaryl or aralkyl with up to 10 C atoms,
characterized in that the PU prepolymer is one based on aromatic
polyisocyanates and polyester polyols based on ethylene glycol or glycerine and
15 aromatic polycarboxylic acids with a hydroxyl number of 100 to 300 and a
hydroxy functionality of 2 to 4, and the prepolymer component is substantially
halogen-free.
- 20 2. A pressure can according to claim 1, characterized in that the
polyisocyanate is one based on naphthalene-1,5-diisocyanate, tolylene
diisocyanate or diphenylmethane diisocyanate.
3. A pressure can according to claim 1 or 2, characterized in that the
polyester polyols have a molecular weight of 1000 to 2000.
4. A pressure can according to one of the preceding claims,
characterized by a content of liquid polybutadiene of 0.01 to 2 wt%.

These claims
are not to
be entered.

RS 12/12/03

COPY

corresponding
EP CLAIMS

2

5. A pressure can according to claim 4, characterized in that the liquid polybutadiene contains about 75% 1,4-cis double bonds, about 24% 1,4-trans double bonds and about 1% vinyl double bonds and has a molecular weight, determined by vapor-pressure osmosis, of about 3000 and a viscosity at 20°C of about 3000 mPa·s.

6. A pressure can according to one of the preceding claims, characterized by a propellant content of 5 to 40 wt%.

7. A pressure can according to one of the preceding claims, characterized in that the propellant component contains propane, butane and/or dimethylether.

8. A pressure can according to one of the preceding claims, characterized in that the propellant component contains fluorocarbon.

9. A pressure can according to one of the preceding claims, characterized in that it additionally contains a flame-retardant additive which is free from chlorine and bromine.

10. A pressure can according to claim 9, characterized in that the flame-retardant additive is melamine, melamine cyanurate, dimelamine phosphate, melamine phosphate, cyanodiamide, dicyanodiamide, aluminum trihydrate, ammonium polyphosphate or a mixture thereof.

11. A pressure can according to one of the preceding claims, characterized by an initial service viscosity of the PU prepolymer at 20°C of 5000 to 20000 mPa·s.

12. A pressure can according to claim 11, characterized by an initial service viscosity of the PU prepolymer of 8000 to 15000 mPa·s.